

LLUMAR ENERGY SAVING WINDOW FILM PERFORMANCE DATA



	% Total Solar Transmittance	% Total Solar Reflectance	% Total Solar Absorbance	% Visible Light Transmittance	% Visible Reflectance (exterior)	% Visible Reflectance (interior)	Winter Median U-value	Shading Coefficient	% Ultraviolet Rejected	Emissivity	Solar Heat Gain Coefficient	% Total Solar Energy Rejected	Light-to-Solar Heat Gain Ratio	% Summer Solar Heat Gain Reduction	% Winter Heat Loss Reduction	% Glare Reduction
Window without film applied (1/8" clear single pane)	83	8	9	90	8	8	1.03	1.00	29	0.84	0.86	14	1.05	0	0	0
REFLECTIVE																
Reflective films feature reflectance on both interiors and exteriors for superior reduction in summer cooling costs and heat retention in winter. Providing a high level of glare and heat control, they are scratch-resistant, shield 99% of ultraviolet rays, and are available in earthtones, skytones, silver, and gold to meet your aesthetic goals.																
RN-07G SR PS (One-Way Mirror)	6	53	41	5	60	14	0.91	0.20	99	0.59	0.16	84	0.31	80	12	94
R-15B SR CDF (Bronze)	10	35	55	10	19	60	0.94	0.28	99	0.70	0.24	76	0.42	72	9	89
R-15G SR CDF (Gray)	9	33	58	7	13	61	0.94	0.29	99	0.70	0.25	75	0.28	71	9	92
R-15BL SR PS (Blue)	10	38	52	11	25	62	0.94	0.29	99	0.70	0.25	75	0.44	71	9	88
R-15GO SR PS (Gold)	11	50	39	14	52	64	0.94	0.25	99	0.70	0.21	79	0.67	75	9	84
R-20 SR CDF (Silver)	12	54	34	16	62	62	0.94	0.25	99	0.71	0.21	79	0.76	75	9	82
R-35 SR CDF (Silver)	21	43	36	28	46	49	0.96	0.40	99	0.73	0.31	69	0.90	60	7	69
R-50 SR CDF (Silver)	36	29	35	48	28	26	0.97	0.54	99	0.75	0.46	54	1.04	46	6	47
DUAL-REFLECTIVE																
Dual-Reflective films are highly reflective on the exterior, lower on the interior, which helps provide clear day and night views. Traditionally specified on commercial buildings, Dual-Reflective films are also popular for sunbelt residential applications. They are scratch-resistant, shield 99% of ultraviolet rays, and provide excellent heat rejection.																
DR-15 SR CDF	16	37	47	15	37	13	0.92	0.30	99	0.63	0.26	74	0.58	70	11	83
DR-25 SR CDF	25	26	49	22	27	13	0.92	0.41	99	0.61	0.35	65	0.63	59	11	76
DR-35 SR CDF	35	19	46	36	19	13	0.93	0.52	99	0.61	0.44	56	0.82	48	10	60
DR-45 SR CDF	47	10	43	47	9	8	1.00	0.69	99	0.78	0.59	41	0.80	31	3	48
LOW-E																
Low-E film provides superior energy conservation by reducing winter heat loss through windows. It is scratch-resistant, shields 99% of ultraviolet rays, reduces glare, and has the highest heat rejection performance of all LLumar films. It is suitable for commercial and residential applications where summer and winter energy control are major concerns.																
E-1220 SR CDF (Silver)	8	58	34	12	66	70	0.77	0.18	99	0.36	0.15	85	0.80	82	25	87
DELUXE																
Deluxe films are specified for commercial buildings where high levels of heat rejection and glare reduction are needed. Deluxe films are ideal for privacy applications and exterior aesthetics. They are scratch-resistant, reduce 99% of ultraviolet rays, and come in gray, green and bronze.																
DL-05G SR CDF (Gray)	14	25	61	6	13	13	0.92	0.35	99	0.62	0.30	70	0.20	65	11	93
DL-15B SR CDF (Bronze)	27	13	60	14	8	8	0.98	0.45	99	0.77	0.39	61	0.36	55	5	84
DL-15G SR CDF (Gray)	26	15	59	16	9	10	0.99	0.45	99	0.78	0.42	58	0.38	55	4	82
DL-30GR SR PS (Green)	29	20	51	30	17	17	0.98	0.53	99	0.76	0.46	54	0.65	47	5	67
NEUTRAL																
Neutral films reduce glare, provide moderate heat rejection and are specified where a soft, neutral appearance is desired. These films are made with sputtered technology, creating a film that allows for very uniform visible light transmission. Neutral films are scratch-resistant and shield 99% of ultraviolet rays.																
N-1020 SR CDF (Neutral)	21	26	53	24	29	28	1.03	0.44	99	0.84	0.37	63	0.65	56	0	73
N-1040 SR CDF (Neutral)	36	16	48	40	18	15	1.00	0.59	99	0.81	0.50	50	0.80	41	3	56
N-1050 SR CDF (Neutral)	44	13	43	49	14	12	1.03	0.67	99	0.84	0.58	42	0.84	33	0	46
N-1065 SR CDF (Neutral)	65	9	26	67	10	9	1.03	0.82	99	0.84	0.71	29	0.94	18	0	26
N-1020B SR CDF (Bronze)	12	49	39	20	37	35	0.93	0.27	99	0.69	0.23	77	0.87	73	10	78
N-1035B SR CDF (Bronze)	25	37	38	37	25	23	0.94	0.41	99	0.71	0.36	64	1.03	59	9	59
N-1050B SR CDF (Bronze)	44	21	35	55	15	14	0.96	0.63	99	0.73	0.54	46	1.02	37	7	39
EXTERIOR																
Exterior Series products are applied to the exterior facing glazing and are highly reflective to provide excellent heat rejection performance without affecting interior reflectance.																
RK-20 PS (Silver)	10	67	23	15	67	62	1.04	0.20	99	0.71	0.17	83	0.88	80	-1	83
UV CLEAR																
UV Clear film is the ideal solution for protecting valuables from sun damage. It provides the highest protection against harmful ultraviolet rays without altering glass aesthetics.																
UV CL-SR PS (Clear)	81	9	10	89	9	9	1.03	0.97	99.9	0.83	0.84	16	1.06	3	0	1
SPECTRALLY-SELECTIVE																
Spectrally Selective films provide a virtually invisible appearance, energy savings, aesthetics, and up to 74% visible light transmission. These films are the top choices for exclusive retail and prime commercial real estate.																
LS-65GN SR CDF (Green)	41	6	53	62	7	7	1.02	0.65	99	0.83	0.56	44	1.11	35	1	31
LS-75GN SR CDF (Green)	48	8	44	74	8	8	0.99	0.70	99	0.79	0.60	40	1.23	30	4	18

The solar performance data reported for LLumar architectural window films was captured using the National Fenestration Rating Council's (NFRC) standard guidelines for window film solar performance measurement as measured on single pane, 1/8 inch (3mm), clear glass. All values averaged from routinely accumulated quality control data.

© 2011 Solutia Inc., St. Louis, Missouri, U.S.A. All rights reserved. LLumar and LLumar Logo are trademarks of Solutia Inc. and/or its affiliates. As used herein, © denotes registered trademark status in the U.S. only. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose, or of any other nature are made hereunder with respect to information or the product to which information refers. Printed in U.S.A. 1/11